PL 300

PROTECTION MAT





PL 300 is a multi-coloured needle punched non-woven geotextile that is thermally reinforced on both sides and weighs 300 g/ $\rm m^2$. It is made of 100 % recycled synthetic rot-proof material with polypropylene being the dominant component.

The excellent combination of needle puncture and thermal treatment during the manufacturing process results in the PL product range that offer unrivalled CBR puncture and tensile strengths for the protection of the underlying waterproofing and root-resistant layers on a green roof.

The PL range offers outstanding mechanical properties at low weights per unit area thus ensuring maximum performance per unit cost. PL 300 is the ideal choice for guarding the waterproofing under extensive green roofs with a growing medium depth below 15 mm as advised in the FLL Guidelines.

Use

Usage of the PL 300 layer include:

- Guarding the waterproofing from physical damage
- Retention of excess water once the growing medium and the drainage boards are saturated
- Gradual release of absorbed water through diffusion

Application area

PL 300 is primarily used to serve protection purposes in an extensive green roof build-up, i.e. to guard the root barrier or the root-resistant waterproofing from physical damage. An overlapping of at least 150 mm is required between the adjacent protection mats. Openings must be cut in the protection mat above the roof outlets.

Size (L x W x H) 50 x 2 x Ø0.35 m

/eight 30 k

Material Recycled synthetic fibres

Colour Multi-colo
Robustness class GRK 2
CBR puncture 1 kN
Cone drop test 24 mm

Tensile strength

Warp (MD) 2.7 kN/m
Weft (CMD) 3.7 kN/m

Elongation at break


Warp (MD) 85% Weft (CMD) 70%

Water permeability

Velocity Index VI_{H50} 95 mm/s

Installation example


Carefully selected vegetation SDS extensive substrate FL 150 filter layer SedumDrain® 25 water reservoir & drainage layer PL 300 protection layer Root-resistant waterproofing Insulation



Specification suggestion

ArchiGreen® PL 300 is a multi-coloured protection mat made of rot-proof recycled synthetic staple fibres needled to form a mesh that reserves structural stability and durability. It is primarily used to fulfil protection purposes on an extensive green roof. Size: $50 \times 2 \times 0.35$ m (L x W x H) [EN ISO 9863]. Weight: 30 kg [EN ISO 9864]. Effective pore size: 0.134 mm [EN ISO 12956]. Static puncture i.e. CBR test: 1kN [EN ISO 12236]. Dynamic perforation test i.e. cone drop test: 24 mm [EN ISO 13433]. Tensile strength warp (MD): 2.7 kN/m; weft (CMD): 3.7 kN/m [EN ISO 10319]. Elongation at break warp (MD): 8%; weft (CMD): 70 % [EN ISO 10319]. Water permeability normal to the plane - velocity index VI_{H50}: 95 mm/s [EN ISO 11058]. Robustness class: GRK 2. Protection performance of the mat exceeds the requirements set forth in the German FLL Guidelines. Delivery and installation is in accordance with manufacturer's instructions.

Technical illustration



Tools required

For safety purposes a hook cutter is advised when cutting the nonwovens. Never cut directly on the waterproofing or the root barrier.

Packaging unit

PL 300 is despatched in rolls of 2 x \varnothing 0.35 m each with the PL 300 protection mat being rolled on carboard tubes and the whole roll is wrapped in a black polyethylene bag. Weight: 30 kg/roll